


## EPDM Rubber Washer 2-3/4" OD x 1/2" ID x 1/2" Thick

Flat die-cut washer · Ethylene propylene diene monomer (EPDM) · 60-70 Shore A · -40°F to 257°F

### DIMENSIONED DRAWING

Units: inches [mm] · Not to scale: use the dimensions



### DIMENSIONS

| Feature               | Nominal | Decimal | Metric   | Tolerance (typical)                   |
|-----------------------|---------|---------|----------|---------------------------------------|
| Outside diameter (OD) | 2-3/4"  | 2.750"  | 69.85 mm | ±0.015" (±0.38 mm)                    |
| Inside diameter (ID)  | 1/2"    | 0.500"  | 12.70 mm | ±0.015" (±0.38 mm)                    |
| Thickness (T)         | 1/2"    | 0.500"  | 12.70 mm | ±0.015" or ±10%, whichever is greater |

### MATERIAL: EPDM

|               |                                         |
|---------------|-----------------------------------------|
| Polymer       | Ethylene propylene diene monomer (EPDM) |
| Hardness      | 60-70 Shore A (typical)                 |
| Service temp. | -40°F to 257°F (-40°C to 125°C)         |
| Colour        | Black                                   |
| Reference     | ASTM D2000 type AA/BA/CA                |

Best weathering of the common washer rubbers; the usual choice for water, outdoor and roofing hardware.

### CHEMICAL RESISTANCE (typical)

| Media                  | Rating      |
|------------------------|-------------|
| Water                  | ■ Excellent |
| Steam / hot water      | ■ Good      |
| Petroleum oil & grease | ■ Poor      |
| Gasoline / diesel      | ■ Poor      |
| Ozone, UV & weather    | ■ Excellent |
| Dilute acids           | ■ Excellent |
| Dilute alkalis         | ■ Excellent |
| Ketones (MEK, acetone) | ■ Good      |

### AVOID

Petroleum oils, fuels and hydrocarbon solvents (EPDM swells).

### TYPICAL USES

- Potable and hot water fittings
- Roofing and outdoor fasteners
- Garden hose and irrigation
- Glycol coolant and brake-fluid service

### Order, bulk price tiers & CAD

|                |                                                                           |
|----------------|---------------------------------------------------------------------------|
| Product page   | <a href="#">Buy this washer (price tiers apply at 50+ pcs)</a>            |
| CAD (2D DXF)   | <a href="#">dixonappstudio.com/specs/rww/RWSHREPD2341212.dxf</a>          |
| CAD (3D STEP)  | <a href="#">dixonappstudio.com/specs/rww/RWSHREPD2341212.step</a>         |
| Material guide | <a href="#">rubberwasherwarehouse.com/pages/epdm-rubber-washers-guide</a> |



Scan to order

TYPICAL VALUES, VERIFY FOR YOUR APPLICATION. Properties are typical for commercial-grade material and are not a specification or warranty; actual values vary by compound, grade, temperature, pressure and exposure time. Test parts in your application before production use. Food-contact, potable-water, flame or electrical ratings apply only when a certified grade is confirmed on your order.

Typical ranges compiled from ASTM D2000 material classes, the Parker O-Ring Handbook (ORD 5700) compatibility tables and Rubber Washer Warehouse material pages.